SZG 24mm□□□

□□□□□□□□

1□ □□□□□□□□□

3□ □□□□

SZG

Professional glass manufacturer

SHENZHEN SUN GLOBAL GLASS CO., LIMITED

Double silver LOW-E glass thermal parameter sheet

GLASS COMPOSITION	Basic Glass	Color	Visible Light Transmittance	Visible Light Reflectance (outdoor)	Visible Light Reflectance (indoor)	America ASHRAE				China JGJ				Europe CEN
						U Value (Winter Night)	U Value (Summer Daytime)	shading coefficient (SC)	Solar Heat Gain Coefficient (SHGC)	RHG	U-Value (W/m2*k)	shading coefficient (SC)	Total Solar Transmittance (G)	U-Value (W/m2*k)
6SZGTN0182+12A+6C	Clear	Neutral	70.00	11.00	12.00	1.65	1.59	0.45	0.39	298.00	1.66	0.49	0.42	1.60
6SZGNE0172+12A+6C	Clear	Grey	65.00	10.00	11.00	1.67	1.61	0.42	0.37	279.00	1.68	0.46	0.39	1.62
6SZGNE0158+12A+6C	Clear	Grey	54.00	15.00	17.00	1.66	1.60	0.35	0.31	236.00	1.67	0.39	0.33	1.61
6SZGTB0170+12A+6C	Clear	Blue	63.00	14.00	16.00	1.64	1.58	0.38	0.33	253.00	1.65	0.42	0.36	1.59
6SZGTB0162+12A+6C	Clear	Blue	57.00	14.00	17.00	1.65	1.59	0.35	0.31	234.00	1.66	0.39	0.33	1.60
6SZGTG0148+12A+6C	Clear	Blue grey	45.00	17.00	18.00	1.65	1.59	0.31	0.27	206.00	1.66	0.34	0.29	1.60
6SZGBG0148+12A+6C	Clear	Silver Grey	42.00	24.00	24.00	1.66	1.61	0.29	0.25	197.00	1.67	0.32	0.27	1.62
6SZGBG0160+12A+6C	Clear	Blue grey	51.00	19.00	11.00	1.67	1.62	0.33	0.29	222.00	1.69	0.37	0.31	1.63
6SZGBG0150+12A+6C	Clear	Silver Grey	43.00	27.00	12.00	1.64	1.59	0.27	0.24	184.00	1.66	0.30	0.26	1.60
6SZGBG0140+12A+6C	Clear	Silver Grey	37.00	28.00	12.00	1.67	1.62	0.25	0.21	168.00	1.68	0.27	0.23	1.63
6SZGNE0168+12A+6C	Clear	Grey	60.00	11.00	11.00	1.64	1.59	0.35	0.30	231.00	1.66	0.38	0.33	1.60

□□□□□□□□

1.□□□□□Sun Global Glass□□□□□□□□

Material Storage Area

Cutting Process

Edgeworks & Drilling

Tempered Process

Ceramic Frit

Insulated Process

Merging Room

Autoclave

Inspection

Packing

Loading

□□□□□□□□□□

CCLU 522582 3
42G1