SGG [illegible] 6 mm - [illegible]

[illegible] [illegible] [illegible] [illegible] [illegible]e[illegible] [illegible] [illegible] [illegible]

[illegible]:

1. [illegible]: [illegible] [illegible] 80% [illegible] [illegible]

2. [illegible]: [illegible] [illegible]

3. [illegible] [illegible]

4. [illegible]: [illegible]

[illegible] 6mm [illegible] [illegible]

1 [illegible] 6mm [illegible]

2 [illegible] 6mm [illegible] [illegible] [illegible] [illegible]

3. [illegible] 6mm [illegible] [illegible] [illegible] [illegible] [illegible]

[illegible]:

1. [illegible]: 3 mm 4 mm 5 mm 5.5 mm 6 mm 8 mm 10 mm 12 mm

2. [illegible]: [illegible] [illegible] [illegible] [illegible] [illegible]

3. [illegible]: 2140 × 3300[illegible]1650 × 2140[illegible]1830 x 2440 2250 x 3300[illegible] [illegible]

[illegible]:

[illegible] 6mm [illegible]

[illegible] 6mm

[illegible]:

□□□ □□□ □□□□ □□□ 6 mm □□□:

Item	Thickness	Visible Light Transmittance	Visible Light Reflectance	UV Light Transmittance	Direct Sunlight Transmittance	Direct Sunlight Reflectance	Total Solar Transmittance	Shdowing Coffecient (SC)	SHGC	K Value (Summer Daytime)	K Value (Winter Night)
Euro Bronze	5 mm	51.94%	6.44%	14.52%	51.78%	6.69%	62.50%	0.70	0.84	0.640	5.272
	6 mm	47.15%	6.73%	11.83%	46.87%	6.79%	58.83%	0.66	0.83	0.606	5.243
Euro Grey	5 mm	51.66%	6.36%	20.29%	49.19%	6.48%	60.63%	0.68	0.84	0.623	5.272
	6 mm	45.24%	6.06%	16.47%	42.98%	6.15%	56.11%	0.63	0.84	0.582	5.243
Dark Grey	5 mm	47.90%	6.77%	19.87%	46.96%	6.75%	58.91%	0.66	0.84	0.606	5.272
	6 mm	41.96%	6.59%	16.54%	41.37%	6.53%	54.82%	0.62	0.83	0.569	5.243
Light Blue	5 mm	71.07%	7.78%	26.60%	53.99%	6.94%	64.07%	0.72	0.654	5.272	5.843
	6 mm	67.74%	7.69%	24.13%	50.67%	6.96%	61.61%	0.69	0.632	5.243	5.808
French Green	5 mm	74.86%	8.03%	24.54%	48.75%	6.67%	60.26%	0.68	0.619	5.272	5.843
	6 mm	71.36%	7.66%	20.22%	43.72%	6.35%	56.60%	0.64	0.586	5.243	5.808

□□□□□:

思路决定出路
GRENZEBACH

□□□□□□□□□□□:

□□□□□□□□□□□ □□□□□□□ □□□□□□□□□□□□□ **6mm** □□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□